

UNIVERSIDADE DE SÃO PAULO

INSTITUTO DE FÍSICA  
CAIXA POSTAL 20516  
01498 - SÃO PAULO - SP  
BRASIL

# publicações

IFUSP/P 441  
B.I.F. - USP

IFUSP/P-441



THE HYPERFINE FIELD AT Na IN Fe

by

A. Hryniewicz

Instytut Fizyki Jadrowej, Kraków, POLAND

R.V. Ribas, M.N. Rao, E.W. Cybulska, W.A. Seale  
and J.C. Acquadro

Instituto de Física, Universidade de São Paulo

and

W.R. Wylie

Centro Técnico Aeroespacial, IEAv/FEX, C.P.6044  
12200 São José dos Campos, SP, Brasil

Dezembro/1983

THE HYPERFINE FIELD AT Na IN Fe

A. Hryniewicz

Instytut Fizyki Jadrowej, Kraków, POLAND

R.V.Ribas, M.N.Rao, E.W.Cybulska, W.A.Seale and J.C.Acquadro  
Laboratório Pelletron, Departamento de Física Nuclear  
Universidade de São Paulo, C.P.20516, 01498 São Paulo, S.P - BRASIL

and

W.R. Wylie

Centro Técnico Aeroespacial, IEAV/FEX, C.P. 6044  
12200 São José dos Campos, S.P. - BRASIL

PACS NUMBER: 76.80. + y

In this note the results of TDPAD measurements for  $^{22}\text{Na}$  nuclei recoil implanted into magnetized iron are reported.

The 583-keV,  $J^\pi = 1^+$  isomeric level was populated by means of the  $^{12}\text{C}(^{14}\text{N}, \alpha)^{22}\text{Na}^*$  reaction at the incident energy of 32 MeV. The half-life of this level was known<sup>1)</sup> to be  $243 \pm 2$  ns. Perturbed angular correlation measurements<sup>1,2)</sup> of the  $0^+ \xrightarrow{73.9\gamma} 1^+ \xrightarrow{583\gamma} 3^+$  cascade had yielded for the g-factor of this level a value of  $+0.529 \pm 0.008$ . The target used in the present experiment consisted of  $1 \text{ mg/cm}^2$  aquadag deposited on a 0.5 mil thick natural iron foil mounted in the gap of a C-magnet which pro-

duced a field of about 300 gauss to saturate the Fe foil. The  $^{14}\text{N}$  beam was pulsed with a repetition period of 800 ns. The delayed time spectrum of the 583-keV gamma rays was measured with two NaI(Tl) scintillation detectors placed at  $\pm 45^\circ$  to the beam direction using conventional fast-slow electronics with a time resolution of  $\sim 5$  ns. The Ratio  $R(t)$  obtained with the normalized difference in counting rates for the two field directions was fitted to the function  $A \sin 2 \omega_L t$ . As the amplitude of the observed oscillations did not exceed  $\sim 1.5\%$ , data were obtained for a total of 70 hours with an average beam current of 3 nA of pulsed beam. A typical  $R(t)$  curve obtained is shown in figure 1. The period of Larmor precession obtained as an average over all the runs was found to be  $(383 \pm 14)$  ns. The effective hyperfine field is then determined from the relation  $H_{\text{eff}} = H_{\text{obs}} - H_{\text{ext}} + H_{\text{DM}}$  where  $H_{\text{ext}}$  is the external field (0.3 kG) and  $H_{\text{DM}}$  the demagnetizing field, the latter assumed negligible for the geometry used.

We obtain a value of  $6.5 \pm 0.3$  kG for the effective magnetic field acting on Na nuclei in Fe. Taking into account the Lorentz field value in Fe of 7.2 kG at room temperature the hyperfine field at Na in Fe is estimated to be  $-1.5 \pm 0.3$  kG.

Two of us, J.C. Acquadro and M.N. Rao, acknowledge partial financial support from the Conselho Nacional de Pesquisas (CNPq).

REFERENCES

1. A.W. Sunyar and P. Thieberger, Phys.Rev. 151, 910 (1966).
2. J. Bleck, D.W. Haag and W. Ribbe, Jahresbericht, Hahn Meirner Institut, p.28 (1967).

